

# Concento metal structure technology – Longline

Combination technique with textured linear surface and a metallic effect with Creativ Lucento 83



The illustration depicts a version of the creative technique and is intended to give an impression of the surface effect to be achieved. The use of the color shade “old bronze” is not mandatory. A variety of other color suggestions can be found at: [brillux.com/applications/interior-design/creative-techniques](https://brillux.com/applications/interior-design/creative-techniques)

Substrate: smoothly filled and primed

Intermediate coat: Adhesion Primer 3720, color shade 03.03.12

Filler application and modeling: Creativ Granulato 71, color shade 03.03.12

First glaze application: Creativ Lucento 83, color shade 03.CM.12

Second glaze application: Creativ Lucento 83, color shade 03.CM.18

## Field of application

For high-quality individual designs, preferably on closed individual areas indoors. For the design of representative wall surfaces such as exclusive wall mirrors and decorative surfaces in e.g. hotel facilities, spa and wellness areas, restaurants, offices, shops as well as in up-market living spaces.

## Characteristics

Harmonious combination technique of textured surface with quartz-filled emulsion paint (brush-on render) and matching effect paint with a metallic, iridescent surface gloss. The selected background shade in combination with the two matching metallic effect shades forms the basis for the special multi-colored effect on the linear modeled surface with directionality. The direction of the lines determines the appearance of the finished surface.

## Application

### Substrate characteristics

The substrate must be smooth, solid, dry, clean, load-bearing and, depending on the substrate condition, filled with e.g. Briplast Silafill 1886.

### Prime coat

When using this creative technique on absorbent substrates, always prime with Lacryl Deep Primer 595 regardless of the subsequent intermediate coat.

### Intermediate coat

Apply Adhesion Primer 3720 in the coordinated color shade evenly with the Polyamide Inking Rollcoater 1314 in a sufficient layer thickness. In working with different substrates with different absorption behavior, the intermediate coat must be applied twice.

### Filler application and modeling

After the intermediate coat has dried sufficiently, apply Creativ Granulato 71, tinted, with Notched Trowel 3768, notch 4 x 4 x 4 mm and comb through in the desired direction. In doing so, keep the notches in a straight line and drag evenly in one direction. Only apply as much render material as can be processed (modeled) within the open time. The direction of the notched trowel texture already determines the orientation and course of the subsequent line texture. The linear design can be executed horizontally, vertically or individually. Immediately after application, model the still wet plaster layer in the selected direction using the Plaster Texture Brush 3121 to create the linear appearance. To do this, move the brush in the direction of the notch structure with light, even pressure over the surface. Due to the limited range during processing, only a certain distance can be textured in a straight line in one go. At the end of the textured section, remove the Plaster Texture Brush 3121 from the surface, reapply and continue texturing as described. When applying the Plaster Texture Brush 3121, arrange it in a wild offset over the entire surface so that no consistent pattern is visible over the entire surface. After removing the Plaster Texture Brush 3121, always remove excess material from the bristles by wiping. Do not continue working on the finished textured surfaces. Allow surfaces to dry.

## Application

- Intermediate sanding** After sufficient drying sand the textured surfaces e.g. with the Mirka DEROS Orbit Sander 5650CV, 3305 (80 grit), including dust extraction, so that the raised areas in the texture are removed and smoothed. Replace the sanding discs regularly after sanding an area of approx. 2 m<sup>2</sup>. Thoroughly sweep the area.
- First glaze application** Apply Creativ Lucento 83 in the selected color shade with the Polyamide Inking Rollcoater 1314 in a sufficient layer thickness in the specified texture orientation and blend with constant changes of direction. Do not form even, straight paths.
- Second glaze application and scraping** Once the surfaces have dried sufficiently (at least 24 hours), apply the final coat and scrape the decorative effect paint in the selected contrasting color.  
To do this, apply Creativ Lucento 83 in the coordinated shade, diluted with approx. 15% water, using the Microfiber Paint Roller 1221 in the specified texture direction and blend individually.  
Immediately after application, scrape the surfaces with the wide edge of the Rubber Float 3766, applying light pressure in alternating directions without a recognizable rhythm. When scraping, frequently change direction and reposition the Rubber Float 3766. For a lap mark-free surface appearance, remove the glaze from the raised areas quickly and only once. Repeating the process can lead to lap marks. Do not completely remove the glaze to zero. If necessary, clean the edge of the Rubber Float.

<b>Adhesive tapes</b>	Apply adhesive tapes directly before each pass and remove them right away.
<b>Implementation of large and contiguous areas</b>	<p>As a general rule, the individual steps should always be carried out by a single person because each worker has their own personal creative style.</p> <p>For larger areas, it is essential to work in a team of several people. In this case, work is carried out on the surface together, one after the other, and each worker carries out the respective step individually. In the case of particularly large surfaces, e.g. room heights of over 2.50 m, it may be necessary for several people to work together on one step. In this case, the work of all persons involved must be coordinated.</p>
<b>Concento color rendering</b>	<p>When looking at the surface from different perspectives, an iridescent color effect can be seen. The individual color tones can be perceived with flowing transitions. The intensity of this effect depends on which color shades are combined. As a rule, two different metallic Lucento 83 shades are applied to a plain background. The color tone of the creative technique results from the interplay of the two shades of Lucento 83 with the background shade. A variety of color suggestions for the creative technique Concento is provided here:</p> <p><a href="https://brillux.com/applications/interior-design/creative-techniques">brillux.com/applications/interior-design/creative-techniques</a></p>
<b>Creating sample surfaces</b>	<p>When creating a sample surface, the work steps and sequences must be followed exactly as for the subsequent execution of the technique. The absorbency of the substrate or the substrate of the sample surface must correspond to the surfaces for the technique to be executed. If necessary, the sample surface must be prepared in advance. It might also be necessary to embed a wall nonwoven or to fill the wall surfaces.</p>
<b>Assessment using sample surfaces</b>	<p>The described implementation of this technique is a tried-and-true standard variant that can be modified depending on the creativity of the individuals. The overall appearance of a creative technique is influenced by color selection and combination, technique execution and the individual “creative handwriting” of the person applying it. We recommend preparing test areas in advance to assess the overall appearance.</p>
<b>Further information</b>	Read and follow the instructions in the Data Sheets of the products to be used.

## List of materials and tools

### • Smoothing and priming the substrate

Briplast Silafill 1886	Approx. 1.0 l/m <sup>2</sup>
Stainless Steel Trowel 1150	
Lacryl Deep Penetrating Primer 595	Approx. 150–200 ml/m <sup>2</sup>
Decorator's Ceiling Brush 1172	

### • Intermediate coat

Adhesion Primer 3720	Approx. 130–150 ml/m <sup>2</sup> (per coat)
Polyamide Inking Rollcoater 1314	

### • Filler application and modeling

Creativ Granulato 71, tinted	Approx. 2200 g/m <sup>2</sup>
Notched Trowel 3768, notching 4 x 4 x 4 mm	
Plaster Texture Brush 3121	

### • Intermediate sanding

Mirka DEROS orbital sander 5650CV, 3305	
Mirka Iridium abrasive discs, 150 mm diameter, 1441, 80 grit	Approx. 0.25 pieces/m <sup>2</sup>

### • First glaze application

Creativ Lucento 83	Approx. 170 ml/m <sup>2</sup>
Polyamide Inking Rollcoater 1314	

### • Second glaze application and scraping

Creativ Lucento 83	approx. 120 ml/m <sup>2</sup> (unthinned)
Microfiber Paint Roller 1221, width 18 cm	
Rubber Float 3766	

## Remark

This information is based on many years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this Data Sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux  
Weseler Straße 401  
48163 Münster  
GERMANY  
Phone +49 251 7188-0  
Fax +49 251 7188-105  
info@brillux.de  
www.brillux.com