

## Floortec PU Hardener 571



Special hardener for Floortec 2K-Sentopur 570

### Field of application

Exclusively for mixing with Floortec 2K-Sentopur 570

### Properties

Special system hardener. The container size has been adapted to the mixing ratio.

### Material description

<b>Color shade</b>	Transparent
<b>Base material</b>	Isocyanate
<b>Flash point</b>	+203°C
<b>Density</b>	Approx. 1.15 g/cm <sup>3</sup>
<b>Packaging</b>	5 kg (Base material and hardener in separate containers)

### Use

<b>Mixing</b>	Stir Floortec 2K-Sentopur 570 evenly before adding the hardener. Mix the base component and hardener in the specified mixing ratio for at least 2 minutes shortly before application. Then transfer to a clean empty container and stir again. Ensure that the hardener container is completely emptied without residue. Follow the instructions in the Floortec 2K-Sentopur color 570 data sheet.
<b>Compatibility</b>	Can only be mixed with materials specified in this data sheet.

## Use

- Application temperature** Do not apply with to max. air, substrate and material temperature below +8°C and over +25°C nor in direct sunlight, at high humidity ( $\geq 80\%$ ) or damp. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point.
- Tool cleaning** Clean tools immediately after use with PUR Thinner 617.

## Storage

Cool, dry, and frost-free between +5°C and +35°C in a well-ventilated area. Reseal opened containers tightly.

## Declaration

- Product code** PU10  
Comply with the specifications in the current safety data sheet.

## Notes

- Further information** Follow the instructions in the data sheets of the products used.

## Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux  
Weseler Straße 401  
48163 Münster  
GERMANY  
Phone +49 251 7188-0  
Fax +49 251 7188-105  
info@brillux.de  
www.brillux.com