

Floortec PU Hardener 879



Special hardener for Floortec 2K-Purolid T 876, Floortec 2K-Purolid T 877 and Floortec 2K-Purolid F 878

Field of application

For mixing with Floortec 2K-Purolid T 876 and Floortec 2K-Purolid T 877 as well as Floortec 2K-Purolid F 878.

Properties

Special system hardener. The container size has been adapted to the mixing ratio.

Material description

Color shade	Colorless
Base material	Aliphatic polyisocyanate
Flash point	+61°C
Density	Approx. 1.09–1.13 g/cm ³
Packaging	125 ml, 500 ml (Base enamel and hardener are supplied separately)

Use

Mixing Thoroughly and evenly stir Floortec 2K-Purolid T 876, Floortec 2K-Purolid T 877 and Floortec 2K-Purolid F 878 before adding the hardener. Mix the base component and hardener in the specified mixing ratio shortly before application. The container sizes correspond to this mixing ratio. Ensure that the hardener container is completely emptied without residue. Observe the information in the Floortec 2K-Purolid T 876, Floortec 2K-Purolid T 877 and Floortec 2K-Purolid F 878 data sheets.

Compatibility Can only be mixed with materials specified in this data sheet.

Use

- Application temperature** Do not apply with to max. air, substrate and material temperature below +8°C and over +25°C nor in direct sunlight, at high humidity ($\geq 80\%$), rainfall, fog, damp, strong wind or on hot surfaces. Take the dew point temperature into consideration. Do not apply unless the temperature is at least 3°C above the dew point.
- Tool cleaning** Clean tools immediately after use with water and Universal Cleaner 1032.

Storage

Cool, dry, and frost-free between +5°C and +35°C in a well-ventilated area. Reseal opened containers tightly.

Declaration

- Product code** PU30
Comply with the specifications in the current safety data sheet.

Notes

- Further information** Follow the instructions on the data sheets of the products used.

Remark

This data sheet is based on extensive development work and years of practical experience. The translation corresponds to the current German version, in compliance with the German laws, regulations, standards and guidelines. Its content does not constitute a contractual legal relationship. The user/buyer is not released from the responsibility of checking our products to ensure they are suitable for the intended application. In addition, our general terms of business apply.

When a new version of this data sheet with updated information is published, the previous version no longer applies. The current version is available on our website.

Brillux
Weseler Straße 401
48163 Münster
GERMANY
Phone +49 251 7188-0
Fax +49 251 7188-105
info@brillux.de
www.brillux.com